

Serial No.: 09/913,501

IN THE CLAIMS:

1. to 76. (Canceled)

77. (Currently Amended) A polymer battery module packaging sheet for packaging a polymer battery module, comprising, as essential components:

a base layer,

an aluminum layer,

a chemical conversion coating, and

an innermost layer;

wherein (1) the innermost layer includes an adhesive resin layer, and

(2) the chemical conversion coating is formed by ~~phosphate treatment using~~ from an aqueous solution comprising a mixture of a phenolic resin, a trivalent chromium phosphate fluoride compound, and phosphoric acid.

78. (Canceled)

Serial No.: 09/913,501

79. (Previously Presented) The polymer battery module packaging sheet according to claim 77, wherein the innermost layer further includes an innermost resin layer.

80. (Canceled)

81. (Previously Presented) The polymer battery module packaging sheet according to claim 79, wherein

the adhesive resin layer is formed of an acid-modified polypropylene resin, the innermost resin layer is formed of a polypropylene resin, and the adhesive resin layer and the innermost layer are formed by a coextrusion lamination method.

82. (Previously Presented) The polymer battery module packaging sheet according to claim 79, wherein

the adhesive resin layer is formed of an acid-modified polypropylene resin, the innermost resin layer is a film of a polypropylene resin, and the adhesive resin layer and the innermost resin layer are formed by a sandwich lamination method.

Serial No.: 09/913,501

83. (Previously Presented) The polymer battery module packaging sheet according to claim 79, wherein

the adhesive resin layer contains an acid-modified polypropylene resin, the innermost resin layer contains an ethylene-butene-propylene terpolymer, and the adhesive resin layer and the innermost layer are formed by a coextrusion lamination method.

84. (Previously Presented) The polymer battery module packaging sheet according to claim 77, wherein an additional chemical conversion coating is interposed between the base layer and the aluminum layer.

85. (Canceled)

86. (Previously Presented) The polymer battery module packaging sheet according to claim 77, wherein the innermost resin layer is formed of an ethylene-rich polypropylene resin.

87. (Canceled)

88. (Previously Presented) The polymer battery module packaging sheet according to claim 79, wherein

the adhesive resin layer is formed of a material containing an acid-modified polypropylene resin as a principal component, the innermost resin layer includes a layer formed of an ethylene-rich random polypropylene resin having an ethylene content in the range of 5% to 10% by mol, and the adhesive resin layer and the innermost resin layer are formed by a sandwich lamination method.

89. (Currently Amended) A polymer battery module packaging sheet manufacturing method comprising the steps of:

processing at least one of a surface of an aluminum layer by chemical conversion treatment;

dry-laminating a base layer to one of the surfaces of the aluminum layer;

forming a laminated sheet by laminating a film consisting of an adhesive resin layer and an innermost layer and formed by a coextrusion lamination method to the surface processed by the chemical conversion treatment of the aluminum layer so that the adhesive resin layer faces the aluminum layer, and then cooling

Serial No.: 09/913,501

~~the adhesive resin layer at a temperature not higher than a softening point of the adhesive resin layer~~ by passing the laminated sheet between a chill roll and a pressure roll; and

heating the laminated sheet so that the adhesive resin layer is heated at a temperature not lower than its softening point ~~and not higher than its melting point.~~

90. (Currently Amended) A polymer battery module packaging sheet manufacturing method comprising the steps of:

processing at least one of a surface of an aluminum layer by chemical conversion treatment;

dry-laminating a base layer to one of the surfaces of the aluminum layer;

forming a laminated sheet by bonding a polypropylene resin film with an adhesive resin layer of an acid-modified polypropylene resin to the other surface processed by the chemical conversion treatment of the aluminum layer by a sandwich lamination process so that the adhesive resin layer faces the aluminum layer, and then cooling the adhesive resin layer ~~at a temperature not higher than a softening point of the~~

Serial No.: 09/913,501

~~adhesive resin layer~~ by passing the laminated sheet between a chill roll and a pressure roll; and

heating the laminated sheet so that the adhesive resin layer is heated at a temperature not lower than its softening point ~~and not higher than its melting point.~~

91. (Currently Amended) A polymer battery module packaging sheet manufacturing method comprising the steps of:

processing at least one of a surface of an aluminum layer by chemical conversion treatment;

dry-laminating a base layer to one of the surfaces of the aluminum layer;

forming a laminated sheet by laminating a film consisting of a film of an adhesive resin layer of an acid-modified polyethylene resin and a film of a polyethylene resin to the surface processed by the chemical conversion treatment of the aluminum layer by a coextrusion lamination method so that the adhesive resin layer faces the aluminum layer, and then cooling the adhesive resin layer ~~at a temperature not higher than a softening point of the adhesive resin layer~~ by passing the laminated sheet between a chill roll and a pressure roll; and

Serial No.: 09/913,501

heating the laminated sheet so that the film of the acid-modified polyethylene resin is heated at a temperature not lower than the softening point of the acid-modified polyethylene resin ~~and not higher than its melting point.~~

92. (Currently Amended) A polymer battery module packaging sheet manufacturing method comprising the steps of:

processing at least one of a surface of an aluminum layer by chemical conversion treatment;

dry-laminating a base layer to one of the surfaces of the aluminum layer;

forming a laminated sheet by bonding a film of a polyethylene resin with an adhesive resin layer of an acid-modified polyethylene resin to the surface processed by the chemical conversion treatment of the aluminum layer by a sandwich lamination process so that the adhesive resin layer faces the aluminum layer, and then cooling the adhesive resin layer ~~at a temperature not higher than a softening point of the adhesive resin layer~~ by passing the laminated sheet between a chill roll and a pressure roll; and

Serial No.: 09/913,501

heating the laminated sheet so that the adhesive resin layer is heated at a temperature not lower than the softening point of the acid-modified polyethylene resin ~~and not higher than its melting point.~~

93. (Currently Amended) A polymer battery module packaging sheet manufacturing method comprising the steps of:

processing at least one of a surface of an aluminum layer by chemical conversion treatment;

dry-laminating a base layer to one of the surfaces of the aluminum layer;

forming a laminated sheet by laminating a film consisting of a film of an adhesive resin layer of an acid-modified polypropylene resin and a film of an ethylene-rich random polypropylene resin to the surface processed by the chemical conversion treatment of the aluminum layer by a coextrusion lamination method so that the adhesive resin layer faces the aluminum layer, and then cooling the adhesive resin layer ~~at a temperature not higher than a softening point of the adhesive resin layer~~ by passing the laminated sheet between a chill roll and a pressure roll; and



Serial No.: 09/913,501

heating the laminated sheet so that the adhesive resin layer is heated at a temperature not lower than the softening point of the acid-modified polypropylene resin ~~and not higher than its melting point.~~

94. (Currently Amended) A polymer battery module packaging sheet manufacturing method comprising the steps of:

processing at least one of a surface of an aluminum layer by chemical conversion treatment;

dry-laminating a base layer to one of the surfaces of the aluminum layer;

forming a laminated sheet by bonding a film of an ethylene-rich random polypropylene resin with an adhesive resin layer of an acid-modified polypropylene resin to the surface processed by the chemical conversion treatment of the aluminum layer by a sandwich lamination process so that the adhesive resin layer faces the aluminum layer, and then cooling the adhesive resin layer ~~at a temperature not higher than a softening point of the adhesive resin layer~~ by passing the laminated sheet between a chill roll and a pressure roll; and

Serial No.: 09/913,501

heating the laminated sheet so that the adhesive resin layer is heated at a temperature not lower than the softening point of the resin layer ~~and not higher than its melting point.~~

95. (Previously Presented) The polymer battery module packaging sheet manufacturing method according to claim 90, wherein both surfaces of the aluminum layer are processed by a chemical conversion treatment.

96. (Previously Presented) The polymer battery module packaging sheet manufacturing method according to claim 91, wherein both surfaces of the aluminum layer are processed by a chemical conversion treatment.

97. (Currently Amended) The polymer battery module packaging sheet manufacturing method according to claim 95, wherein both the surfaces of the aluminum layer are processed by a chemical conversion treatment, using an aqueous solution comprising a mixture of a phenolic resin, a trivalent chromium phosphate fluoride compound, and phosphoric acid.

98. (Previously Presented) The polymer battery module packaging sheet manufacturing method according to claim 93, wherein the polypropylene resin is a multilayer structure including at least one layer of an ethylene-rich random polypropylene resin.

99. (Previously Presented) The polymer battery module packaging sheet manufacturing method according to claim 94, wherein the polypropylene resin is a multilayer structure including at least one layer of an ethylene-rich random polypropylene resin.

100. (Currently Amended) A polymer battery module packaging sheet manufacturing method, comprising the steps of:

processing one of a surface of an aluminum layer by chemical conversion treatment;

dry-laminating the aluminum layer to a base layer with the other surface of the aluminum layer not processed by the chemical conversion treatment bonded to the base layer;

forming an innermost layer on the surface processed by the chemical conversion treatment of the aluminum layer by extruding

Serial No.: 09/913,501

a molten resin for forming the innermost layer in a molten resin film by an extrusion method and then cooling the innermost layer by passing the innermost layer between a chill roll and a pressure roll, and

heating the innermost layer at a temperature not lower than its softening point.

101. (Previously Presented) The polymer battery module packaging sheet manufacturing method according to claim 100, wherein a surface of the molten resin film facing the aluminum layer is processed by ozone treatment when forming the innermost layer.

102. (Previously Presented) The polymer battery module packaging sheet manufacturing method according to claim 90, wherein a surface of the adhesive resin layer facing the aluminum layer is processed by ozone treatment when forming the laminated sheet.

103. to 110. (Canceled)